PATENT ABSTRACTS OF JAPAN

(11)Publication number:

11-003813

(43) Date of publication of application: 06.01.1999

(51)Int.CI.

H01F 1/34

CO1G 49/00

CO4B 35/30

(21)Application number: 09-155205

(71)Applicant : KAWASAKI STEEL CORP

(22)Date of filing:

12.06.1997

(72)Inventor: KONO TAKASHI

FUJITA AKIRA GOTO SATOSHI

(54) FERRITE MATERIAL

(57)Abstract:

PROBLEM TO BE SOLVED: To provide a ferrite material which can be effectively reduced in loss, by simultaneously mixing NiO and CoO in the fundamental component of an Mn-Zn ferrite containing Fe2O3 in excess of a specific amount.

SOLUTION: A ferrite material contains a basic component composed of about 52 to 68 mol.% Fe2O3, about 0.5 to 10 mol.% NiO, about 15 mol.% or less ZnO, about 0.05 to 0.5 mol.% CoO, and the remaining mol.% MnO. It is possible to mix 0.010–0.100 wt.% SiO2 and 0.020–0.300 wt.% CaO in the basic component, and, in addition, to mix one or two kinds of oxides selected from among Nb2O5, Ta2O5, V2O5, ZrO2, HfO2, TiO2, and SnO2 in the basic component within specific ranges. However, the total content of these added components must be adjusted to ≤ 1 wt.%. When the total content of the added components is adjusted to ≤ 1 wt.%, the value of the loss of the ferrite material at 1 MHz, 50 mT, and 80° C becomes ≤ 300 kW/m3. Therefore, a ferrite material which



is less in loss in a high-frequency domain can be obtained.

LEGAL STATUS

[Date of request for examination]

31.07.2002

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

3597673

[Date of registration]

17.09.2004

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office